



EPO-SET Standard Viscosity Epoxy Resin Mounting Compound



MetPrep's Standard Viscosity Epoxy Cold Mounting compound is a two part system comprising a resin and a hardener.

Ideal when the ultimate edge retention is required. Curing time is typically 4 - 5 hours at room temperature.

11 10 61 EPO-SET Resin 1 Kg
11 10 66 EPO-SET Hardener 0.25 Kg

Mixing Instructions

Four Parts Resin - 1 Part Hardener by weight

Mounting moulds of assorted sizes, mixing cups and stirring sticks are also available

Shelf life typically 12 months

MetPrep Technical Data Sheet 0003 - 2019. For further information please contact sales@metprep.co.uk

MetPrep Ltd - Falklands Close, Charter Avenue, Coventry, CV4 8AU - 02476 421222